

Overview Sylomer®

by getzner
sylomer®

Material

mixed-cell PU elastomer (polyurethane) with combined spring and dampening properties

Standard delivery dimension

Thickness: 12.5 mm / 25 mm

Roll: 1.5 m wide, 5.0 m long

Strip: up to 1.5 m wide, up to 5.0 m long

Other dimensions, punched and moulded parts on request.

Sylomer® Material type

SR
11

SR
18

SR
28

SR
42

SR
55

SR
110

SR
220

SR
450

SR
850

SR
1200

Material properties	Test methods										
Colour		yellow	orange	blue	pink	green	brown	red	grey	turquoise	winered
Static range of use ¹ in N/mm ²		0.011	0.018	0.028	0.042	0.055	0.110	0.220	0.450	0.850	1.200
Load peaks ¹ in N/mm ²		0.50	0.75	1.00	2.00	2.00	3.00	4.00	5.00	6.00	6.00
Mechanical loss factor	DIN 53513 ²	0.25	0.23	0.21	0.18	0.17	0.14	0.13	0.12	0.11	0.11
Rebound resilience in %	EN ISO 8307	40	40	45	55	55	55	55	60	60	60
Compression ³ set in %	EN ISO 1856 ²	<5	<5	<5	<5	<5	<5	<5	<5	<5	<5
Static modulus of elasticity ¹ in N/mm ²		0.06	0.08	0.19	0.22	0.34	0.83	1.47	3.36	7.23	9.37
Dynamic modulus of elasticity ¹ in N/mm ²	DIN 53513 ²	0.20	0.29	0.42	0.60	0.75	1.52	2.58	5.42	11.08	15.62
Static shear modulus in N/mm ²	DIN ISO 1827 ²	0.04	0.06	0.07	0.09	0.11	0.22	0.38	0.58	0.84	0.94
Dynamic shear modulus in N/mm ²	DIN ISO 1827 ²	0.10	0.12	0.14	0.17	0.20	0.34	0.57	0.82	1.15	1.28
Min. tensile stress at rupture in N/mm ²	DIN EN ISO 527-3/5/500 ²	0.30	0.35	0.40	0.50	0.55	0.85	1.20	1.70	2.30	2.50
Min. tensile elongation at rupture in %	DIN EN ISO 527-3/5/500 ²	250	230	200	190	190	180	170	160	150	150
Abrasion ³ in mm ³	DIN ISO 4649	≤1,400	≤400	≤1,300	≤1,200	≤1,100	≤1,100	≤1,000	≤400	≤300	≤350
Coefficient of friction (steel)	Getzner Werkstoffe	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
Coefficient of friction (concrete)	Getzner Werkstoffe	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7
Specific volume resistance in Ω·cm	DIN EN 62631-3-1 ²	>10 ¹⁰	>10 ¹⁰	>10 ¹⁰	>10 ¹⁰	>10 ¹⁰	>10 ¹⁰	>10 ¹⁰	>10 ¹⁰	>10 ¹⁰	>10 ¹⁰
Thermal conductivity in W/mK	DIN EN 12667	0.045	0.050	0.050	0.055	0.060	0.075	0.090	0.110	0.130	0.140
Temperature range in °C		-30 to 70									
Temperature peak in °C	short term ⁴	120									
Flammability	EN ISO 11925-2	class E/EN 13501-1									

¹ Values apply to shape factor q=3

² Measurement/evaluation in accordance with the relevant standard

³ The measurement is performed on a density-dependent basis with differing test parameters

⁴ Application-specific

All information and data is based on our current knowledge. The data can be applied for calculations and as guidelines, are subject to typical manufacturing tolerances and are not guaranteed. Material properties as well as their tolerances can vary depending on type of application or use and are available from Getzner on request.

Further information can be found in VDI Guideline 2062 (Association of German Engineers) as well as in glossary. Further characteristic values on request.